

## 2012 Second Quarter Production Summary for the Bolivar Mine

	Three	Three months ended			Six months ended		
	June 30, 2012	June 30, 2011	% Var.	June 30, 2012	June 30, 2011	% Var.	
Tonnes processed (t)	86,061	28,415	203%	148,010	54,395	172%	
Daily throughput	1,043	344	203%	897	330	172%	
Copper grade	1.21%	1.51%	-20%	1.17%	1.33%	-12%	
Zinc grade	2.51%	7.94%	-68%	2.66%	7.52%	-65%	
Silver grade (g/t)	24.38	50.29	-52%	26.52	44.94	-41%	
Copper recovery	82.94%	86.04%	-4%	82.59%	86.43%	-4%	
Zinc recovery	80.12%	88.28%	-9%	80.08%	88.29%	-9%	
Silver recovery	77.74%	74.99%	4%	76.78%	71.39%	8%	
Silver (oz)	52,544	34,585	52%	96,903	56,708	71%	
Copper (000 lbs)	1,910	814	135%	3,154	1,373	130%	
Zinc (000 lbs)	3,817	4,392	-13%	6,954	7,966	-13%	

## **Corporate Address**

TSX.V: DIB

Suite 2900, 330 Bay Street

**BVL: DIB** 

Toronto, ON, Canada M5H 2T4

www.diabras.com